



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

912-1 LAVAL CRESCENT — KAMLOOPS, B.C.
V2C 5P5

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Energy, Mines & Resources

CANMET, Mineral Sciences Laboratories,
555 Booth St.,
Ottawa, Ont.
K1A 0G1

Attn: Mr. H.F. Steger

TITLE: Certification of Zn/Al Alloys

Certificate No. K 6687

Date March 26, 1985.

Contract # 05Q84-00173

I hereby certify that the following are the results of assays made by us upon the herein described samples

Kral No	Marked	Al	Cu	Mg	Fe	Cd	Pb	Sn
		%	%	ppm	%	ppm	ppm	ppm
1	NZA-1 Bottle #137	31.95	1.53	212	.042	10	39	82
2		31.93	1.52	206	.043	10	37	84
3		31.94	1.55	208	.043	10	33	83
4		31.73	1.55	210	.051	10	38	83
5		31.93	1.55	208	.046	10	37	84
6	NZA-2 Bottle #84	26.20	3.09	280	.020	47	74	52
7		26.16	3.06	283	.022	46	79	58
8		26.34	3.14	277	.021	46	75	53
9		26.19	3.07	282	.021	47	75	58
10		26.22	3.07	281	.020	47	78	57
11	NZA-3 Bottle #140	27.73	2.09	92	.066	63	50	53
12		27.76	2.08	90	.068	63	49	53
13		27.91	2.05	90	.066	63	46	58
14		27.85	2.05	87	.069	62	44	53
15		27.87	2.08	91	.061	63	46	54
16	NZA-4 Bottle #79	27.84	2.55	104	.026	29	90	100
17		27.93	2.57	108	.026	29	91	100
18		27.88	2.57	106	.029	29	90	101
19		27.75	2.59	106	.028	29	90	94
20		27.70	2.57	108	.026	30	92	98

JUL 13 1985

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

2 pp
Derek A. Blumfeld

Steroid Assayer, Province of British Columbia

MICROMEDIA



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

912 - 1 LAVAL CRESCENT — KAMLOOPS, B.C.
V2C 5P5

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Energy, Mines & Resources

Certificate No. K 6687 2

Date March 26, 1985.

I hereby certify that the following are the results of assays made by us upon the herein described samples

Kral No.	Marked	Al	Cu	Mg	Fe	Cd	Pb	Sn
		%	%	ppm	%	ppm	ppm	ppm
21	NZA-5 Bottle #70	10.91	1.07	226	.017	95	21	20
22		10.93	1.07	226	.017	94	23	20
23		10.84	1.06	228	.015	94	22	20
24		10.66	1.08	227	.016	94	20	20
25		10.79	1.06	227	.017	95	22	19
26	NZA-6 Bottle #66	7.69	3.26	21	.015	142	827	52
27		7.63	3.23	19	.017	142	818	56
28		7.63	3.27	21	.018	141	821	52
29		7.58	3.27	20	.017	140	820	53
30		7.66	3.24	19	.018	141	821	54
31	NZA-7 Bottle #74	12.25	.24	491	.012	2	129	112
32		12.22	.22	488	.012	2	131	112
33		12.30	.24	488	.010	2	131	112
34		12.34	.23	485	.010	2	134	113
35		12.29	.23	486	.012	2	140	113
Method: Aqua-regia digestion, atomic absorption analysis.								

NOTE:
Rejects retained three weeks.
Pulp retained three months
unless otherwise arranged.

Deke A. Blundell
Registered Assayer, Province of British Columbia